

TEST REPORT

Ceram Reference: 113875 (QT-18405/1/JB) /Ref.01

Project Title: Performance Testing of Butyl Strip Sealant

Client: Specialist Technical Products Ltd

For The Attention of: Mr Peter Bolton

Author(s): Mr Dave Dix

Report Date: 14 September, 2011

Purchase Order No.: 1329

Work Location: Ceram UK



Miss Joanne Booth
Consultancy Team
REVIEWER



Mr Dave Dix
Consultancy Team
PROJECT MANAGER

This report is issued in accordance with the Conditions of Business of Ceram Research Limited and relates only to the sample(s) tested. No responsibility is taken for the accuracy of the sampling unless this is done under our own supervision. This report shall not be reproduced in part without the written approval of Ceram Research Limited, nor used in any way as to lead to misrepresentation of the results or their implications.

Ceram is the trading name of Ceram Research Limited
A subsidiary of British Ceramic Research Limited Registered in England No. 1960455 Registered Office as above.

AB

Ceram
Test Report
Laboratory No.113875/Ref.01

CONTENTS

- 1 INTRODUCTION**
- 2 PROCEDURE**
- 3 RESULTS**
- 4 CONCLUSIONS**

**Ceram
Test Report
Laboratory No.113875/Ref.01**

1 INTRODUCTION

Specialist Technical Products Ltd provided samples of butyl strip sealant for use in the test programme. The strip sealant had nominal dimensions of 9mm x 3mm and was pale grey in colour.

This report summarises the results of a series of tests carried out on the sealant to determine its performance before and after accelerated ageing, cyclic shear loading, and water retention.

2 PROCEDURE

The tests were carried out in accordance with the methods stated in Test Methods 1 to 5 based on the methods given in Appendix 1 of NFRC/FRA Technical Bulletin 36.

The results of the tests are given in Table 1.

3 RESULTS

The results of the tests are summarised in Table 1.

4 CONCLUSIONS

The strip sealant as tested achieved a classification of Class A (See Table 1).

Table 1 - Performance Data of Butyl Strip Sealant

Test Number/Description	Test Results		Performance Classification
Test 1 – Adhesion/Cohesion before and after artificial heat ageing	No loss of adhesion when the joint is extended by 30% of its compressed thickness before and after ageing		A
Test 2 – Low force static shear	Separated by less than 5mm after 7 days when subjected to 50g mass.		A
Test 3 – Water resistance	No leaks during test period		A
Test 4 – Compression	Max compression 1.50kgcm ² when tested at 23°C (Limit = 1.5kgcm ²)	Max compression 1.57kgcm ² when tested at 5°C (Limit = 2.5kgcm ²)	A

Test 5 – Shear retention before and after ageing/cyclic testing	Mean shear strength 103.4N before ageing	Mean shear strength 78.6N (76%) after ageing	A
---	--	--	---